Effects of CsI and/or SnBr₂ Additions to CH₃NH₃PbI₃ Perovskite Solar Cells

Naoki Ueoka, Takeo Oku*, Atsushi Suzuki

Department of Materials Science, the University of Shiga Prefecture, Japan

Copyright©2017 by authors, all rights reserved. Authors agree that this article remains permanently open access under the terms of the Creative Commons Attribution License 4.0 International License

Abstract Perovskite-type CH₃NH₃(MA)PbI₃-based photovoltaic devices were fabricated and characterized. Effects of cesium iodide (CsI) and/or tin bromide (SnBr₂) additions on the photovoltaic properties and microstructures of the perovskite solar cells were investigated. The open-circuit voltage increased with CsI addition because of increase of the band gap energy. The short-circuit current densities and the external quantum efficiencies increased by CsI and SnBr₂ addition because of decrease of series resistance, which resulted in the improvement of photovoltaic performance of the perovskite solar cells. X-ray diffraction indicated the doped elements existed in the perovskite crystals. The cell prepared by a starting composition of MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} showed the best photovoltaic performance in the present work.

Keywords Perovskite Solar Cells, CsI, SnBr₂

1. Introduction

Hybrid organolead halide perovskites have a composition of ABX₃, where A is organic or inorganic cation such as CH₃NH₃⁺ (MA⁺), HC(NH)₂⁺ (FA⁺) or Cs⁺, B is metal cation (Pb²⁺ or Sn²⁺) and X is halogen (I⁻, Br⁻ or Cl⁻), and they have been extensively investigated as light absorbers. The perovskite solar cells are expected as next generation solar cells because of absorption in the whole range of visible light of 300–800 nm and high hole mobility. In addition, spin-coating is a simple and low-cost fabrication method [1-13]. Sn-doped perovskite solar cells have been reported to have low band gap energy (E_g), and the current density increased [14-17]. On the other hands, the E_g increased by Cs⁺ doping to MA⁺ [1].

The purpose of the present work is to fabricate and characterize the CH₃NH₃PbI₃ (MAPbI₃), MA_{0.95}Cs_{0.05}PbI₃, MAPb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1}, MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} solar cells to investigate effects of CsI and/or SnBr₂ additions to the MAPbI₃ phase. In the previous work [18], simultaneous

addition of CsI, CsBr and SnBr₂ to MAPbI₃ was effective for improvement of surface coverage of the perovskite crystals for the cell, which resulted in the increase of the short-circuit current density, the fill factor and the conversion efficiency. In the present work, the detailed fabrication and analysis of the devices were performed by measuring internal quantum efficiencies, UV-vis absorbance and microstructures using X-ray diffraction (XRD).

2. Materials and Methods

A schematic illustration of the fabrication process of the present perovskite photovoltaic cells is shown in Fig. 1. The detailed fabrication process is described in the previous reports [18-21]. F-doped tin oxide (FTO) substrates were cleaned using an ultrasonic bath with acetone and methanol, and dried under nitrogen gas. 0.15 M and 0.30 M TiO₂ precursor solutions were prepared from titanium diisopropoxide bis (acetyl acetonate) (0.055 mL and 0.11 mL) with 1-butanol (1 mL). The 0.15 M TiO_x precursor solution was spin-coated on the FTO substrate at 3000 rpm for 30s and annealed at 125°C for 5 min. Then, the 0.30 M TiO_x precursor solution was spin-coated on the TiO_x layer at 3000 rpm for 30s and annealed at 125°C for 5 min. The process of 0.30 M precursor layer was performed two times. The FTO substrate was sintered at 500°C for 30 min to form a compact TiO₂ layer. After that, TiO₂ paste was spin-casted on the compact TiO₂ by spin-coating at 5000 rpm for 30 s. For the mesoporous TiO₂ layer, the TiO₂ paste was prepared with TiO₂ powder (P25) with poly (ethylene glycol) (PEG #20000) in ultrapure water [22, 23]. The solution was mixed with acetylacetone (10 μ L) and surfactant triton X-100 (5 μ L) for 30 min, and was left for 24 h to suppress the bubble in the solution. The cells were annealed at 120°C for 5 min and at 500°C for 30 min to form the mesoporous TiO₂ layer [22, 23]. For the preparation of the perovskite compounds, solutions of CH₃NH₃I and PbI₂ with CsI and/or SnBr₂ in γ -butyrolactone (0.3 mL) and *N,N*-dimethylformamide (0.2 mL) was mixed at 60°C. Preparation compositions of the

perovskite phases were MAPbI₃, MA_{0.95}Cs_{0.05}PbI₃, MAPb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1}, MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1}. The solution of the perovskite phase was then introduced into the TiO₂ mesopores by a spin-coating method and annealed at 100°C for 30 min. Then, a hole transport layer (HTL) was prepared by spin-coating. As the HTL, a solution of 2,2',7,7'-tetrakis-(*N,N*-di-*p*-methoxyphenylamine)-9,9'-spirobifluorene (spiro-OMeTAD, 36.1 mg) in chlorobenzene (0.5 mL) was mixed with a solution of lithium bis(trifluoromethylsulfonyl) imide (Li-TFSI, 260 mg) in acetonitrile (0.5 mL) for 24 h. The former solution with 4-tertbutylpyridine (14.4 μL) was mixed with the Li-TFSI solution (8.8 μL) for 30 min at 70°C. All procedures were carried out in air at temperature of ~22°C and at humidity of ~40%. Finally, gold (Au) thin films were evaporated as top electrodes. Layered structures of the present photovoltaic cells are denoted as FTO/TiO₂/perovskite/spiro-OMeTAD/Au, as shown in a schematic illustration of Fig. 1.

The current density–voltage (*J*-*V*) characteristics (Keysight B2-01A) of the photovoltaic cells were measured under illumination at 100 mW cm⁻² by using an AM 1.5 solar simulator (San-ei Electric XES-301S). The solar cells were illuminated through the side of the FTO substrates, and the measurement area was 0.090 cm². The external quantum efficiencies (EQE) and internal quantum efficiencies (IQE) of the cells were investigated (Enli Technology, QE-R). The UV-vis absorbance of the cells also were investigated (Jasco V-770SPU). The microstructures of the perovskite layers were investigated by using an X-ray diffractometer (Bruker, D2 Phaser).

Figure 1. Schematic illustration of fabrication process of the present photovoltaic devices

3. Results and Discussion

J-*V* characteristics of the present FTO/TiO₂/perovskite/spiro-OMeTAD/Au cells under illumination are shown in Fig. 2. Measured photovoltaic parameters of the perovskite solar cells are summarized in Table 1. The standard perovskite solar cell provided a short-circuit current density (*J*_{sc}) of 12.0 mA cm⁻², an open-circuit voltage (*V*_{oc}) of 0.770 V, a fill factor (*FF*) of 0.603, a conversion efficiency (*η*) of 5.59 % and a series resistance (*R*_s) of 9.73 Ω cm⁻². The short-circuit current density and open-circuit voltage increased to 13.5 mA cm⁻² and 0.862 V, respectively, by Cs⁺ doping to the MA⁺ site. The *J*_{sc} value increased to 15.9 mA cm⁻², and *R*_s value decreased to 6.72 Ω cm⁻² by the SnBr₂ addition. Moreover, by the simultaneous addition of CsI and SnBr₂, the short-circuit current density and the open-circuit voltage increased to 16.5 mA cm⁻² and 0.780 V, and the series resistance decreased to 7.23 Ω cm⁻², respectively, which resulted in the improvement of the photovoltaic performance compared with that of the standard MAPbI₃.

EQE and IQE spectra of the present solar cells are shown in Fig. 3(a) and (b), respectively. Photoelectric conversion was observed for the perovskite solar cells in a visible light range, and the EQE increased by the addition of CsI and SnBr₂. The MAPbI₃, MA_{0.95}Cs_{0.05}PbI₃, MAPb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1}, MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} solar cells exhibit the highest EQEs of 18.4% at 580 nm, 21.7% at 580 nm, 26.0% at 690 nm and 27.4% at 560 nm, respectively.

Figure 2. *J*-*V* characteristics of the perovskite solar cell

Table 1. Measured photovoltaic parameters of the perovskite solar cells

Cell	J_{sc} (mA cm ⁻²)	V_{oc} (V)	FF	H (%)	η_{ave} (%)	R_s (Ω cm ⁻²)
MAPbI ₃	12.0	0.770	0.603	5.59	4.55	9.73
MA _{0.95} Cs _{0.05} PbI ₃	13.5	0.862	0.564	6.59	5.04	11.58
MAPb _{0.95} Sn _{0.05} I _{2.9} Br _{0.1}	15.9	0.770	0.586	7.18	6.42	6.72
MA _{0.95} Cs _{0.05} Pb _{0.95} Sn _{0.05} I _{2.9} Br _{0.1}	16.5	0.780	0.584	7.52	7.03	7.23

Figure 3. (a) EQE spectra and (b) IQE spectra of the perovskite solar cells

The IQE values also increased by addition of CsI and SnBr₂. The present EQE and IQE data showed that the current density increased by simultaneous addition of CsI and SnBr₂, which resulted in the increase of carrier generation.

Figure 4. (a) UV-vis absorption spectra and (b) $(h\nu a)^2$ vs photon energies of the perovskite solar cells.

Table 2. Band gap energies of the perovskite solar cells

Cell	Band gap (eV)
MAPbI ₃	1.571
MA _{0.95} Cs _{0.05} PbI ₃	1.581
MAPb _{0.95} Sn _{0.05} I _{2.9} Br _{0.1}	1.590
MA _{0.95} Cs _{0.05} Pb _{0.95} Sn _{0.05} I _{2.9} Br _{0.1}	1.597

UV-vis absorption spectra of FTO/TiO₂/perovskite devices are shown in Fig. 4(a). The absorbance increased by the CsI and/or SnBr₂ addition, and the absorption edges around 800 nm indicate blue shift by the addition. Tauc plots of MAPbI₃, MA_{0.95}Cs_{0.05}PbI₃, MAPb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} and MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} solar cells are shown in Fig. 4(b). The band gap energies of the solar cells are summarized in Table 2. The E_g values increased by the addition of CsI and/or SnBr₂, which resulted in the

improvement of the open-circuit voltage.

XRD patterns of the present perovskite solar cells are shown in Fig. 5(a), and enlarged XRD patterns for the 100 reflection of the solar cells are shown in Fig. 5(b).

Figure 5. (a) XRD patterns of the perovskite solar cells. (b) Enlarged patterns of the 100 reflection.

Table 3. d -values of 100 reflection of the cells

Cell	d (Å)
MAPbI ₃	6.298
MA _{0.95} Cs _{0.05} PbI ₃	6.294
MAPb _{0.95} Sn _{0.05} I _{2.9} Br _{0.1}	6.279
MA _{0.95} Cs _{0.05} Pb _{0.95} Sn _{0.05} I _{2.9} Br _{0.1}	6.269

The d -values of 100 of the perovskite structures are summarized as Table 3. The 100 peak means the Miller index of the perovskite crystal, which corresponds to the lattice constant. The peak of the perovskite crystals were observed, and the lattice constants decreased by the addition of CsI and/or SnBr₂. Since the ionic sizes of CH₃NH₃⁺, Cs⁺, Pb²⁺, Sn²⁺ are 2.70, 1.81, 1.49 and 1.35 Å, respectively [8,15], these elements are believed to be doped in the perovskite crystals. Diffraction peaks corresponding to PbI₂ are also observed for all cells, and are especially high for the cells added with SnBr₂, which might indicates the effectiveness of the PbI₂ phase on the photovoltaic performance by passivation of surface defects [24, 25]. Although the photovoltaic devices showed the best photovoltaic performance of 7.52% for MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1}, the PbI₂ peak is smaller for MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} than for MAPb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} according to XRD pattern in Fig. 5(a), assuming that the 100 peak heights remain the same. This indicates the Cs substitution at the MA sites would be effective for the photovoltaic properties, especially for the J_{SC} values, and the Cs substitution was also confirmed from the decrease of the lattice constant by the addition of Cs, as observed in Table 3.

The MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} photovoltaic devices showed the best photovoltaic performance of 7.52%, which is higher than that of a MASnBr₃ cell [16]. By the addition of 5% SnBr₂ to PbI₂ and/or 5% CsI to MAI, the photovoltaic performances were improved in the present work. The stability of the MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.90}Br_{0.10} device was not so good, which was almost same as that of MAPbI₃. Fabrication of more stable perovskite solar cells is necessary in the future.

4. Conclusions

The MAPbI₃, MA_{0.95}Cs_{0.05}PbI₃, MAPb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1}, MA_{0.95}Cs_{0.05}Pb_{0.95}Sn_{0.05}I_{2.9}Br_{0.1} photovoltaic devices were fabricated and characterized. The open-circuit voltage and short-circuit current density increased by addition of CsI and SnBr₂. The band gap energies increased by CsI, and the the series resistance decreased by adding SnBr₂. The EQE and IQE increased by addition of CsI and SnBr₂. The XRD data indicated doped elements existed in the perovskite crystals.

Acknowledgements

This work was partly supported by Satellite Cluster Program of Japan Science and Technology Agency (JST).

REFERENCES

[1] H. Choi, J. Je, Ha. Kim, S. Kim, Br. Walker, G.Kim, Jin. You,

Nano Energy, 7, 80-85 (2014).

- [2] M. Hu, L. Liu, A. Mei, Y. Yang, T. Liu, H. Han, J. Mater. Chem. A, 40, 17115-17121 (2014).
- [3] C. Zuo, Li. Din, Nanoscale 6, 9935-9938 (2014).
- [4] J. W. Lee, D. H. Kim, H. S. Kim, S. W. Seo, S. M. Cho and N. G. Park, Adv. Energy Mater. 5, 1501310-1-9 (2015).
- [5] T. Oku, Y. Ohishi and A. Suzuki, Chem. Lett., 45, 134-136 (2016)
- [6] D. Bi, W. Tress, M. I. Dar, P. Gao, J. Luo, C. Renevier, K. Schenk, A. Abate, F. Giordano, J. P. C. Baena, J. D. Decoppet, S. M. Zakeeruddin, M. K. Nazzeruddin, M. Grätzel, and A. Hagfeldt, Sci. Adv. 2, 1501170-1-7 (2016).
- [7] W. S. Yang, J. H. Noh, N. J. Jeon, Y. C. Kim, S. Ryu, J. Seo and S. Il. Seok, Science, 348, 1234-1237 (2015).
- [8] M. Saliba, T. Matsui, J.Y.Seo, K. Domanski, M. K. Nazeerudin, S. M. Zakeeruddin, W. Tress, A. Abate, A. Hagfeldt, and M. Grätzel, Energy Environ. Sci., 9, 1989-1997 (2016).
- [9] D. P. McMeekin, G. Sadoughi, W. Rehman, G. E. Eperon, M.Saliba, M. T. Horantner, A. Haghighirad, N. Sakai, L.Korte, B. Rech, M. B. Johnston, L. M. Hetz, and H. J. Snaith, Science 351, 151-155 (2016).
- [10] A. Swarnkar, A. R. Marshall, E. M. Sanhira, B. D. Chernomordik, D. T. Moore, J. A. Christians, T. hakrabarti and J. M. Luther, Science, 354, 92-95 (2016).
- [11] X. Li, D. Bi, C. Yi, J. D. Decoppet, J. Luo, S. M. Zakeeruddin, A. Hagfeldt and M. Grätzel, Science, 353, 58 (2016).
- [12] T. Oku, N. Ueoka, K. Suzuki, A. Suzuki, M. Yamada, H. Sakamoto, S. Minami, S. Fukunishi, K. Kohno and S. Miyauchi, AIP Conf. Proc., 1807, 020014-1-7 (2017).
- [13] T. Matsui, J. Y. Seo, M. Saliba, S. M. Zakeeruddin and M. Grätzel, Adv. Mater., 29, 1606258-1-5 (2017).
- [14] P. Umari, E. Mosconi and F. D. Angelis, Sci. Rep., 4, 4467-1-7 (2014).
- [15] F. Zuo, S. T. Williams, P. W. Liang, C. C. Chueh, C. Y. Liao and A. K. Y. Jen, Adv. Mater., 26, 6454-6460 (2014).
- [16] F. Hao, C. C. Stoumpos, D. H. Cao, R. P. H. Chang and M. G. Kanatzidis, Nat. Photon. 8, 489-494 (2014).
- [17] Xiao Liu, Zhibin Yang, Chu-Chen Chueh, Adharsh Rajagopal, Spencer T. Williams, Ye Sun and Alex K.-Y. Jen, J. Mater. Chem., 4, 17939-17945 (2016).
- [18] N. Ueoka, Y. Ohishi, Y. Shirahata, A. Suzuki, and T. Oku, AIP Conf. Proc. 1807, 020009-1-9 (2017).
- [19] T. Oku, Y. Ohishi, A. Suzuki, and Y. Miyazawa, Metals, 6, 147-1-13 (2016).
- [20] M. Zushi, A. Suzuki, T. Akiyama, and T. Oku, Chem. Lett., 43, 916-918 (2014).
- [21] T. Oku, M. Zushi, Y. Imanishi, A. Suzuki, and K. Suzuki, Appl. Phys. Express, 7, 121601-1-4 (2014).
- [22] T. Oku, K. Suzuki, and A. Suzuki, J. Ceram. Soc. Jpn., 124, 234-238 (2016).

- [23] T. Oku, Y. Ohishi, A. Suzuki and Y. Miyazawa, J. Ceram. Soc. Jpn., 125, 303-307 (2017).
- [24] D. Bi, W. Tress, M. I. Dar, P. Gao, J. Luo, C. Renevier, K. Schenk, A. Abate, F. Giordano, J.-P. C. Baena, J.-D. Decoppet, S. M. Zakeeruddin, M. K. Nazeeruddin, M. Grätzel, and A. Hagfeldt, Sci. Adv., 2, 1501170-1-7 (2016).
- [25] T. Zhang, N. Guo, G. Li, X. Qian, and Y. Zhao, Nano Energy, 26, 50-56 (2016).